

E. obliqua mature

E. obliqua mature

Meter reading	06	07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	
Wood Temp °C	Corrected Moisture Content for Species & Temperature																							
05	10	11	12	13	14	15	16	16	17	18	19	20	21	22										
10	10	11	12	12	13	14	15	16	17	18	18	19	20	21	22									
15	09	10	11	12	13	14	15	16	16	17	18	18	19	20	22									
20	09	10	11	12	12	13	14	15	16	16	17	18	18	19	20	21	22							
25		09	10	11	12	12	13	14	15	16	16	17	18	18	19	20	21	22						
30		09	10	11	12	12	13	14	14	15	16	16	17	18	18	19	20	21	22					
35			09	10	11	12	12	13	14	15	16	16	17	17	18	18	19	20	21	22				
40				09	10	11	12	12	13	14	15	16	16	17	17	18	18	19	20	21	22			
50					09	10	11	12	12	13	13	14	15	16	16	17	18	18	19	19	20	21	22	
60						09	10	11	11	12	12	13	14	15	16	16	16	17	18	18	19	20	20	
70							09	10	11	12	12	13	13	14	15	16	16	17	17	18	18	19		
80								09	10	11	12	12	12	13	14	15	15	16	16	17	18	18		
90									09	10	11	11	12	12	13	13	14	15	16	16	16	17		



with compliments

Timber Research Unit
 School of Architecture, University of Tasmania,
 Locked Bag 1-324, Launceston, Tas, 7250

phone: 03 6324 3133 fax: 03 6324 3141
 email: Timber@arch.utas.edu.au
 web: <http://www.tastimber.tas.gov.au>