

Meter reading	06	07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28
Wood Temp °C	Corrected Moisture Content for Species & Temperature																						
05	08	09	10	11	12	13	14	14	15	16	18	18	19	20									
10	08	09	10	11	11	12	13	14	15	16	17	18	18	19	20								
15	07	08	09	10	11	12	13	14	14	15	16	17	18	18	20								
20	07	08	09	10	11	11	12	13	14	14	15	16	17	18	18	19	20						
25		07	08	09	10	11	11	12	13	14	15	16	17	18	18	19	20						
30		07	08	09	10	11	11	12	12	13	14	14	15	16	17	18	18	19	20				
35			07	08	09	10	11	11	12	13	14	14	15	15	16	17	18	18	19	20			
40				07	08	09	10	11	11	12	13	14	14	15	15	16	17	18	18	19	20		
50					07	08	09	10	11	11	11	12	13	14	14	15	16	17	18	18	18	19	20
60						07	08	09	09	10	11	11	12	13	14	14	14	15	16	17	18	18	18
70							07	08	09	10	11	11	11	12	13	14	14	15	15	16	17	18	
80								07	08	09	10	10	11	11	12	13	13	14	14	15	16	17	
90									07	08	09	09	10	11	11	11	12	13	14	14	14	15	



with compliments

Timber Research Unit
 School of Architecture, University of Tasmania,
 Locked Bag 1-324, Launceston, Tas, 7250

phone: 03 6324 3133 **fax:** 03 6324 3141
email: Timber@arch.utas.edu.au
web: <http://www.tastimber.tas.gov.au>