

E. regnans & *delegatensis*

E. regnans & delegatensis

Meter reading	06	07	08	09	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28		
Wood Temp °C	Corrected Moisture Content for Species & Temperature																								
05	09	10	11	13	14	15	16	17	18	18	20	21	22	23											
10	09	10	11	12	13	14	15	16	18	18	19	20	21	22	23										
15	08	09	10	11	13	14	15	16	17	18	18	19	20	21	23										
20	08	09	10	11	12	13	14	15	16	17	18	18	19	20	21	22	23								
25		08	09	10	11	12	13	14	15	16	17	18	18	19	20	21	22	23							
30		08	09	10	11	12	13	14	14	15	16	17	18	18	19	20	21	22	23						
35			08	09	10	11	12	13	14	15	16	17	18	18	19	20	21	22	23						
40				08	09	10	11	12	13	14	15	16	17	18	18	18	19	20	21	22	23				
50					08	09	10	11	12	13	13	14	15	16	17	18	18	19	20	20	21	22	23		
60						08	09	10	10	11	12	13	14	15	16	16	17	18	18	19	20	21	21		
70								08	09	10	11	12	13	13	14	15	16	17	18	18	18	19	20		
80									08	09	10	11	11	12	13	14	15	15	16	17	18	18	19		
90										08	09	10	10	11	12	13	13	14	15	16	17	17	18		



with compliments
 Timber Research Unit
 School of Architecture, University of Tasmania,
 Locked Bag 1-324, Launceston, Tas, 7250

phone: 03 6324 3133 fax: 03 6324 3141
 email: Timber@arch.utas.edu.au
 web: http://www.tastimber.tas.gov.au